(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication: 14.11.2001 Bulletin 2001/46

(51) Int Cl.7: **B29C 45/14**, B29C 45/44

(21) Application number: 00125740.1

(22) Date of filing: 24.11.2000

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU

MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI


(30) Priority: 12.05.2000 IT TO200443

(71) Applicant: CRS Srl Centro Ricerche e Sperimentazioni 10060 Frossasco (IT) (72) Inventor: Cesano, Franco 10060 San Secondo di Pinerolo (IT)

(74) Representative: Marchitelli, Mauro Buzzi, Notaro & Antonielli d'Oulx Corso Fiume 6 10133 Torino (IT)

(54) Process and equipment for hot moulding of articles made of thermoplastic material

- (57) A process for the hot moulding of articles (L) made of thermoplastic material, comprising the steps of:
- heating at least one plate of thermoplastic material
 (L) to a plasticizing temperature;
- compressing said heated plate (L) between two
- moulding surfaces (14, 16), set opposite one another, of a pair of half-moulds (10, 12); and
- forming, by injection moulding, at least one component (22) anchored to a surface of the plate (L), while the plate is being compressed between said moulding surfaces (14, 16).



Description

[0001] The present invention relates to a process and equipment for the hot moulding of articles made of thermoplastic material.

[0002] The invention has been developed in particular for the moulding of panels for lining the interiors of motor vehicles. A conventional technology for the production of lining panels involves heating of at least one plate of thermoplastic material to a plasticizing temperature and setting the plate, together with a possible upholstery sheet, between two half-moulds of an apparatus for hot moulding, which are provided with respective moulding surfaces set opposite one another. Hot moulding involves the application of pressure on opposite surfaces of the plate in a plastic state, thus bestowing on the plate the desired shape. Normally, during moulding of the plate, also an upholstery sheet is applied on one surface of the plate itself. When panels are produced for internal lining of motor vehicles, it is often necessary to fix, on the rear surface of the panel, one or more inserts forming an anchoring seat for a fixing means, such as a screw, a snap-in pin, or the like. Normally, these inserts are produced by injection moulding separately from the hot moulding of the panel, and are subsequently fixed by welding on the rear surface of the moulded plate. Alternatively, the inserts produced by injection moulding may be fixed on the plate during hot moulding of the plate itself. In this case, the inserts are positioned in the hot-moulding equipment and are mechanically anchored to the plate during moulding.

[0003] The latter approach requires injection-moulding equipment independent of the hot-moulding equipment and involves an operating step in which the inserts are fixed onto the moulded plates, or else a step in which the inserts are positioned on the moulding equipment.

[0004] The object of the present invention is to provide a process and equipment for hot moulding of articles made of thermoplastic material, which will enable a reduction in the cost of the finished articles and a simplification of the production cycle.

[0005] According to the present invention, the above subject is achieved by a process and equipment having the characteristics specified in the claims.

[0006] The present invention will now be described in detail with reference to the attached drawings, which are provided purely to furnish a non-limiting example, and in which:

- Figure 1 is a schematic partial section of hot-moulding equipment according to the present invention;
- Figures 2 and 3 are schematic sections illustrating the equipment of Figure 1 in various steps of the operating cycle;
- Figure 4 is a schematic perspective view of the part indicated by the arrow IV in Figure 3; and
- Figure 5 is a detail at an enlarged scale of the part indicated by the arrow V in Figure 3.

[0007] With reference to Figures 1-3, the numbers 10 and 12 respectively designate a top half-mould and a bottom half-mould of a hot-moulding apparatus. The half-moulds 10, 12 have respective moulding surfaces 14, 16, which are set opposite each other and are designed to apply a moulding pressure on a plate L of thermoplastic material, following upon movement from an open position to a closed position.

[0008] Figure 1 illustrates the half-moulds in a closed position, at the end of hot moulding of the plate L. The plate L is first heated up to a plasticizing temperature and is set between the two half-moulds 10, 12 while these are in the open position. An upholstery sheet R may be set between the two half-moulds together with the plate L so that it will be applied on one surface of the plate L during moulding of the latter. The half-moulds 10, 12 are provided, in a conventional way, with a cooling system in order to ensure that, during the moulding operation, the plate L will be cooled down to a temperature substantially lower than the plasticizing temperature of the thermoplastic material.

[0009] One of the two half-moulds (in the example illustrated, the bottom half-mould 12) is provided with at least one injection-moulding seat 18, which communicates with an injection channel 20. The seat 18 is designed to form an insert 22 having, for instance, the shape illustrated in Figure 4. The insert 22, illustrated to provide an example in Figure 4, comprises a portion 24 containing a hole 26 with its axis substantially orthogonal to the plate L. The portion 24 is connected to the plate L via three walls 28 fixed to the plate L, each along one of its edges 30.

[0010] Figure 1 illustrates the configuration of the moulding equipment at the end of the hot-moulding step and before injection of plastic material into the injection-moulding seat 18. The seat 18 is defined between one portion of the mould 12 and a slider 32 which is mobile with respect to the half-mould 12 to enable extraction of the insert 22 that is formed in the seat 18. The slider 32 has a surface 34 which constitutes a portion of the hot-moulding surface of the half-mould 12.

[0011] As may be seen in Figure 1, the moulding seat 18 communicates with the hot-moulding surface 16, 34 by means of a narrow section 36 which constitutes the joining edge 30 between the insert 22 and the plate L. The narrow section 36 has a surface substantially smaller than that of the transverse section of the remaining part of the cavity 18, so as to produce, at the narrow section 36, a marked reduction in the pressure of the plastic material injected into the moulding seat 18.

[0012] With reference to Figure 2, after hot moulding of the plate L has been completed, and after partial cooling of the plate L by contact with the half-moulds 10, 12, plastic material compatible with the thermoplastic matrix of the plate L is injected into the injection-moulding seat 18. The injection of plastic material is performed according to a technology typical of injection moulding of plastic materials. For example, the plastic material may be pro-

20

25

pylene-based and may be injected at pressures in the region of 600-1000 bar and at a temperature in the region of 180°C. The narrow section 36 of contact between the moulding seat 18 and the plate L reduces the pressure against the plate L of the injected material and thus prevents the injected material from damaging the plate L and the upholstery sheet R. The dimensions of the narrow section 36 can be varied according to the parameters of the injection process so as to prevent damage to the plate and, at the same time, to obtain a surface for mutual fixing between the insert 22 and the plate L that is sufficiently large for providing firm anchorage.

[0013] As illustrated in Figure 3, after the insert 22 has been obtained by injection moulding, the half-moulds 10, 12 are brought into the open position and, at the same time, the slider 32 is displaced with respect to the half-mould 12 in the direction indicated by the arrow A so as to enable extraction of the insert 22 from the seat 18. As illustrated in Figures 3 and 5, the insert 22 is anchored to the plate L along the edge 30 having a narrow section. The number of inserts 22 fixed to the plate L may vary according to the particular requirements. Also the shape and size of each insert 22 may vary widely with respect to what is described and illustrated herein purely for the purpose of providing an example.

Claims

- A process for the hot moulding of articles (L) made of thermoplastic material, comprising the steps of:
 - heating at least one plate of thermoplastic material (L) to a plasticizing temperature; and
 - compressing said heated plate (L) between two moulding surfaces (14, 16), set opposite one another, of a pair of half-moulds (10, 12);

characterized in that it comprises the step of forming, by injection moulding, at least one component (22) anchored to a surface of the plate (L), while the plate is being compressed between said moulding surfaces (14, 16).

- A process according to Claim 1, characterized in that injection moulding of the aforesaid component (22) is performed by injecting plastic material at high pressure into a seat (18) communicating with one of said moulding surfaces (14, 16).
- A process according to Claim 2, characterized in that said seat (18) presents a narrow section (36) designed to produce a reduction in the pressure of the plastic material injected in contact with the plate (L).
- 4. A process according to Claim 1, characterized in

that it comprises the step of displacing a slider (32) defining one part of said seat (18) for extracting the injection-moulded component (32) from the respective seat (18).


- Equipment for hot moulding of articles made of thermoplastic material, comprising:
 - a first half-mould (10) and a second half-mould (12) which are free to move with respect to one another between an open position and a closed position and are provided with respective moulding surfaces (14, 16) designed to carry out hot moulding of at least one plate (L) of thermoplastic material,


characterized in that at least one of said halfmoulds (10, 12) comprises at least one injectionmoulding seat (18) communicating with the respective hot-moulding surface (16, 34), at least one injection channel (20) being provided for injecting plastic material inside said seat (18).


- Equipment according to Claim 5, characterized in that the aforesaid injection-moulding seat. (18) presents a narrow section (36) designed to reduce the pressure of the plastic material injected in contact with the plate (L).
- Equipment according to Claim 5, characterized in that the half-mould (12) provided with said injection-moulding seat (18) carries a slider (32) which is mobile with respect to the half-mould (12) between an operating position in which the slider (32) defines a part of said injection-moulding seat (18) and a non-operating position in which the injection-moulded component can be extracted from the seat (18).

45


50













EUROPEAN SEARCH REPORT

Application Number

EP 00 12 5740

	DOCUMENTS CONSIL				
Category	Citation of document with of relevant par	Indication, where appropriate, scapes	Relevant to claim	CLASSIFICATION OF THE APPLICATION (INCC17)	
X	DE 198 18 881 A (J 5 November 1998 (1		1,2,5	B29C45/14 B29C45/44	
Y	* the whole docume		4,7	829045/44	
X .	PATENT ABSTRACTS 0 vol. 1997, no. 1, 31 January 1997 (1) -& JP 08 229977 A 10 September 1996 * abstract *	997-01-31) (KASAI KOGYO CO LTD),	1,2,5		
Y	FR 2 768 360 A (AL 19 March 1999 (1999 * the whole document	9-03-19)	4,7		
Y	PATENT ABSTRACTS OF vol. 16, no. 471 (130 September 1992 (-2 JP 04 168019 A 6 June 1992 (1992-4 abstract *	4,7	TECHNICAL FIELDS SEARCHED (INLCLT)		
Y	PATENT ABSTRACTS OF vol. 1999, no. 10, 31 August 1999 (199- -& JP 11 123725 A (11 May 1999 (1999- * abstract *	99-08-31) (AISIN CHEM CO LTD),	4,7	B29C	
ı	PATENT ABSTRACTS OF vol. 1997, no. 02, 28 February 1997 (1 ~& JP 08 252838 A (KK), 1 October 1996 * abstract *	1997-02-28) MITSUBISHI ENG PLAST	3,6		
	The present search report has	been drawn up for all claims	-		
	Place of search	Date of completion of the search		Examiner	
	THE HAGUE	17 August 2001	Bo1	len, J	
X : partic Y : partic docu A : techn O : non-	ATEGORY OF CITED DOCUMENTS cutarly relevant if taken alone cutarly relevant if combined with anomalic to the same category totogical background written disclosure modilate document	E : earlier perent after the filing ther D : document cit L : document cit	ciple underlying the in document, but publis	wention Hed on, or	



EUROPEAN SEARCH REPORT

Application Number EP 00 12 5740

	DOCUMENTS CONSIDE	RED TO BE RELEVANT				
Category	Citation of document with in of relevant passe	dication, where appropriate, ages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (INLCL7)		
А	PATENT ABSTRACTS OF vol. 9, no. 70 (M-30 30 March 1985 (1985- & JP 59 201835 A (1985) 15 November 1984 (1984)	57), -03-30) (OJIMA PRESS KOGYO KK),	3,6			
-	-					
	*					
	-			TECHNICAL FIELDS SEARCHED (InLCI.7)		
-		-				
		non drum un der all alaims				
	The present search report has t			Everniner		
	Place of seerch THE HAGUE	Date of completion of the search 17 August 2001	Bol	len, J		
X:pai Y:pai	ATEGORY OF CITED DOCUMENTS ticularly relevant if taken alone ticularly relevant if combined with anoticularly relevant if combined with anoticularly relevant in complete the same calegory	T : theory or princt E : earlier patient of after the filing of D : document cited L : document cited	ole underlying the ocument, but publicate in the application for other reasons	invention ished on, or		
O: no	hnological background n-written disclosure ermedia le document		 member of the same patent tamily, corresponding document 			

EP 1 153 725 A1

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 00 12 5740

This annex lists the patent family members relating to the patent documents cited in the above—mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-08-2001

Patent document cited in search report		rt	Publication date	Patent family member(s)	Publication date
DE	19818881	A	05-11-1998	KR 241127 B CN 1198376 A JP 2964034 B JP 11147261 A	01-02-200 11-11-199 18-10-199 02-06-199
JP	08229977	A	10-09-1996	NONE	
FR	2768360	A	19-03-1999	NONE	
JP	04168019	A	16-06-1992	NONE	
JP	11123725	A	11-05-1999	NONE	· *** -**
JP	08252838	A	01-10-1996	US 5942169 A	24-08-199
JP	59201835	Α	15-11-1984	NONE	

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82